

# PAM-GLOBAL S

## Blank end



### DESCRIPTION

Part of the Standard drainage system, the PAM GLOBAL S blank ends enable you to cap the ends of pipes or fittings. The blank end is made up of cast iron coated with a reddish-brown epoxy film applied by cataphoresis.

### RECOMMENDED USE

- Rainwater
- Valve water
- Wastewater

### STANDARDS & APPROVALS

- Industry Product Standards:
  - DIN EN 877
- Acoustic Performance:  $L_{sc} \leq 10$  dB(A) &  $LaA = 47$  dB(A) according to EN 14366 with 2L/s.
- Range fire classification: A1

### Material & Coatings

- Cast Iron
- Coating: red-brown, anti-corrosive cataphoresis epoxy, average dry film thickness 70  $\mu$ m.

### TECHNICAL FEATURES

- Hot water resistance: 24h at 95°C.
- Thermal cycle resistance: 1500 cycles between 15°C and 93°C.
- Chemical resistance for  $2 \leq pH \leq 12$ .
- Salt spray resistance internal coating: more than 350 h.


### ENVIRONMENTAL DATA

- Percentage of Recycled Content: 99 %
- Recycling Information: Cast iron is 100% recyclable through the existing recycling industrial network.  
Data source: Environmental Product Declaration S-P-02013



# PAM-GLOBAL S

## Blank end



DN	L	H	W	Weight	Product Code
50	58	30	58	0.25	155747
75	83	35	83	0.45	176700
100	110	40	110	0.8	155809
125	135	45	135	1.2	155865
150	160	50	160	1.7	155898
200	210	60	210	3.2	155928
250	274	70	274	5.9	155945
300	326	80	326	10	155957

All dimensions are in mm and nominal weights are in kg

This document is provided for information purposes only and our company reserves the right to modify the information contained herein at any time. Our company declines all responsibility in the event of the use or installation of materials that do not comply with the rules prescribed in this document as well as with the standards, the technical documents and the applicable professional standards. Any orders placed will be subject to our General Terms and Conditions of Sale, available on request. The drawings and/or images are the exclusive property of Saint-Gobain PAM and are confidential. They must not be reproduced or disclosed to any third party without written consent. They may only be used for the purpose for which they were issued and are returnable on request.